



# DA-1200

## Dairen Chemical Corporation

## VAE Redispersible Powder

### PRODUCT SPECIFICATIONS

	Inspection Method	Value
Solids Content	DCC method	99 ± 1%
Ash Content	DCC method	10 ± 2%
Appearance	Visual	White Powder
Tg	DCC method	0±3 °C

### TYPICAL PROPERTY

	Inspection Method	Value
Polymer Type		VinylAcetate-Ethylene copolymer
Protective Colloid		Polyvinyl Alcohol
Bulk Density	DCC method	0.5 g/ml
Average Particle Size	DCC method	90 μm
Viscosity at 25 °C	DCC method	2000 mPa.s
pH	DCC method	7

### Introduction

DA-1200 is a water-redispersible vinyl acetate/ethylene copolymer powder that is readily dispersible in water and forms stable emulsion.

This redispersible powder is especially recommended for blending with inorganic binders such as cement, gypsum and hydrated lime, or as a sole binder for the manufacture of construction adhesives.

### Applications

DA-1200 improves adhesion, flexural strength, abrasion resistance and workability of modified compounds such as tile adhesives, self-leveling compounds and gypsum based compounds.

It is therefore compatible with mortar additives used to achieve special processing characteristics.

DA-1200 contains a fine, mineral filler as anti-block agent. It is free of solvents, plasticizers and film-forming aids.

### Recommended Uses

#### Tile adhesives

For thin-bed tile adhesives with good frost resistance, we recommend using 1~5% DA-1200 and about 0.2 - 0.6 % of cellulose ether or other appropriate cellulose derivatives as water retention agent, and, if necessary, organic fibres to reduce slump. To obtain adhesives with greater plasticity, the proportion of redispersible powder should be increased, the amount of cement reduced.

#### Self-leveling compounds

DA-1200 is suitable for modifying self-leveling flooring compounds. It is thoroughly compatible with all commonly-used superplasticizers, such as condensation products of melamine sulphonic acid and naphthalene sulphonic acid or lignin sulphonates. Addition of the dispersion powder improves adhesion, abrasion resistance, flexural strength, workability and the flow properties of the compounds.

DA-1200 is especially suitable for use in self-leveling flooring compounds which contain casein. The compounds display very high tolerance towards excess water, have little tendency to slump, and have a very smooth, crater-free surface.

DA-1200 is suitable for use with standard inorganic binders such as Portland cement, high-alumina cement, anhydrite, gypsum, lime and mixtures thereof.

#### Gypsum based compounds

The addition of DA-1200 to trowelling compounds and boards containing gypsum as binder increases flexural strength, impact resistance and adhesion. To improve water retention, cellulose ether should be added and ranges from 1 – 6 % DA-1200 based on total weight.



**DA-1200**

**Dairen Chemical Corporation**

**VAE Redispersible Powder**

---

### **Processing**

For the production of powdered products such as dry mortars, tile adhesives, gypsum based compound. DA-1200 redispersible powder is mixed with the dry, finely divided additives in suitable mixers. Pressure or excessive shear in the mixer and the transferring line should be avoided, since this will raise the temperature, leading to agglomeration of the thermoplastic resin particles.

After sufficient water has been added, mortars can be mixed by hand or machine.

Since mixing by hand only generates low shear forces, it is best to allow the mixture to mature by leaving it to stand for 5 minutes, and then to stir it again.

### **Storage**

DA-1200 redispersible powder should be stored in cool and dry environment. It is recommended to use within 6 months, preferably be used as soon as possible in summer. Storage in high temperature and humidity conditions will increase the risk of caking. Opened containers should be used as soon as possible, if not, should be resealed to prevent ingress of moisture from the air.

DA-1200 redispersible powder supplied in paper bags should not be stacked. Prolonged heavy pressure may cause caking. Storage under pressure should also be avoided.

### **Packaging**

25 kg paper bags

Big Bags (450/550/600 kg)

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of products is guaranteed under our General Conditions of Sale. Neither Dairen nor its agents nor its distributors accept liability for damages arising from the use of our product or our recommendation. The recommendations should be evaluated by the customers' different operating conditions and raw materials. It is our customers' responsibility to avoid infringement of the rights of third parties. We reserve the right to modify the document as the technical development.