



PRODUCT SPECIFICATIONS

	Inspection Method	Value
Solids content	DCC method	49-51 %
Viscosity at 25 °C	DCC method	10 - 100 mPa.s
pH	DCC method	5.0- 7.0

TYPICAL PROPERTY

	Inspection Method	Value
Film Appearance	Visual	Clear
Tg	DCC method	28~32 °C
Stabilizing System		Cellulose/Surfactant

INTRODUCTION

DA-905 is an aqueous milky white terpolymer dispersion based on vinyl chloride, vinyl acetate and ethylene. It can form film with aid of the suitable coalescing solvent at the room temperature.

General speaking, DA-905 is used as general adhesive for best adhesion to a wide range of material. DA-905 also provides the fire retardance property for the effect of vinyl chloride content.

In addition, DA-905 possesses the property of crosslinking due to special crosslinkable unit of DA-905. These properties together with the possibility of a reactive cross-linking make the emulsion an ideal base for compounders to formulate special tailor-made high performance adhesives.

DA-905 readily accepts high load of fillers, like calcium carbonate, clay, shell- or wood flours. Viscosity can be increased by blending in PVA or HEC solution. Also polyurethane / polyacrylic based associative thickeners can be recommended without negative side effects.

DA-905 is miscible with all others non-ionic and protective colloid stabilized DA-products of our range, but trials should always be carried out. Dry films may become hazy by mixing different polymers with different refractive indices.

RECOMMENDED APPLICATIONS

As mentioned before, DA-905 is used for broad application in the industry. The crosslinking ability of DA-905 provides strong bonding between substrates. It is noticed, furthermore, DA-905 can not form a tough film at room temperature without aid of coalescing agent.

The most popular use of DA-905 emulsions is for fabrics- and textile-related applications, like

- Nonwoven Fabric Binder
- Paper Impregnation
- Car Sheet and Carpet Backing
- PVC lamination

As EVA-VC emulsions are composed of vinyl chloride and possess the self-quenching effect, they are also used in several fire retardance-related industries.

SAFETY & STORAGE

In general, DA-905 is considered safe for its intended use. However, as this class of products always contains minor amount of residual vinyl acetate monomers, adequate ventilation is recommended in rooms where DA-905 is handled. Generally when working with polymer emulsions, protective clothes, gloves and also goggles should be used. Splashes on the skin or in the eyes should immediately be removed by irrigation with clean water.

DA-905 should be stored in sheltered areas at temperatures between 5 and 40 °C; do never store under freezing conditions. Opened containers should be closed soon to prevent skinning. If the product is stored for a longer period, stirring is recommended before use. Shelf life of DA-905 is minimum 6 months, provided the product is stored in original, unopened containers under proper conditions.

DA-905 is adequately preserved to prevent microbial contamination. However, if the product is kept in original containers which have been opened, or is transferred to other tanks, the product should be added with suitable preservative package to protect it against microbial attack. Equipment and facilities used to transfer the product should also be kept adequately clean. Finished products manufactured from polymer emulsions usually also require preservation.



DA-905

Dairen Chemical Corporation

VAE Emulsion

SAFETY NOTICE

Material Safety Data Sheets are available on request from sales offices or may be printed via web site www.dcc.com.

EVA-VC and EVCL series products are licensed by Sumitomo Chemical Cooperation (Japan). This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of products is guaranteed under our General Conditions of Sale. Neither Dairen nor its agents nor its distributors accept liability for damages arising from the use of our product or our recommendation. The recommendations should be evaluated by the customers' different operating conditions and raw materials. It is our customers' responsibility to avoid infringement of the rights of third parties. We reserve the right to modify the document as the technical development.